



August 19, 2025

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Lot No.: 693521

Date: 8/13/25

BRACE-GRIP® Dead-End CAT. NO.	Strand Size (in.)	Strand RBS (lbs.)	Maximum Load (lbs.)	% of RBS	Failure Mode at Maximum Load
BRG-2583	3/8" EHS G.S.	15,400	16,957	110	Strand broke mid span. No slip from either dead-end.
			16,987	110	Strand broke mid span. No slip from either dead-end.
		AVERAGE	16,972	110	

Regards,

Scott L. Sanderson

Senior Quality Engineer

RMB

cc: File 94, M. Miller

PLP.COM