



February 21, 2025

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Lot No.: 670679

Date: 2/13/25

| BRACE-GRIP®<br>Dead-End CAT.<br>NO. | Strand<br>Size (in.) | Strand<br>RBS (lbs.) | Maximum<br>Load (lbs.) | % of<br>RBS | Failure Mode at Maximum<br>Load                         |
|-------------------------------------|----------------------|----------------------|------------------------|-------------|---------------------------------------------------------|
| BRG-2583                            | 3/8"<br>EHS<br>G.S.  | 15,400               | 17,858                 | 116         | Strand broke mid span.<br>No slip from either dead-end. |
|                                     |                      |                      | 17,860                 | 116         | Strand broke mid span.<br>No slip from either dead-end. |
|                                     |                      | AVERAGE              | 17,859                 | 116         |                                                         |

Regards,

A handwritten signature in black ink that reads "Scott Sanderson". The signature is written in a cursive, flowing style.

Scott L. Sanderson

Senior Quality Engineer

RMB

cc: File 94, M. Miller

PLP.COM