



October 13, 2025

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Lot No.: 693520

Date: 9/2/25

BRACE-GRIP® Dead-End CAT. NO.	Strand Size (in.)	Strand RBS (lbs.)	Maximum Load (lbs.)	% of RBS	Failure Mode at Maximum Load
BRG-2582	5/16" EHS G.S.	11,200	13,384	120	One wire failed at the cross over mark at max load No slip from either dead-end.
			13,674	122	One wire failed at the cross over mark at max load No slip from either dead-end.
		AVERAGE	13,529	121	

Regards,

A handwritten signature in black ink that reads "Scott Sanderson". The signature is written in a cursive, flowing style.

Scott L. Sanderson

Senior Quality Engineer

RMB

PLP.COM



cc: File 94, M. Miller

PLP.COM