

November 7, 2023

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Lot No.: 619414 Date: 10/27/23

| BRACE-GRIP® Dead-End CAT. NO. | Strand Size (in.) | Strand RBS (lbs.) | Maximum Load (lbs.) | % of RBS | Failure Mode at Maximum Load |
|-------------------------------------|----------------------|----------------------|------------------------|-------------|---|
| BRG-2583 | 3/8" | 15,400 | 16,986 | 110 | Strand broke mid span. No slip from either deadend. |
| | G.S. | | 16,950 | 110 | Strand broke mid span. No slip from either dead- end. |
| | | AVERAGE | 16,968 | 110 | |

Regards,

Scott L. Sanderson

Senior Quality Engineer

RMB

cc: File 94, M. Miller