



December 12, 2023

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Lot No.: 597788

Date: 11/22/23

BRACE-GRIP® Dead-End CAT. NO.	Strand Size (in.)	Strand RBS (lbs.)	Maximum Load (lbs.)	% of RBS	Failure Mode at Maximum Load
BRG-2582	5/16" EHS G.S.	11,200	12,272	110	Strand broke mid span. No slip from either dead-end.
			12,272	110	Strand broke mid span. No slip from either dead-end.
		AVERAGE	12,272	110	

Regards,

A handwritten signature in black ink that reads "Scott Sanderson". The signature is written in a cursive, flowing style.

Scott L. Sanderson

Senior Quality Engineer

RMB

cc: File 94, M. Miller

PLP.COM