



# DHARMA

Smooth rubber surface with a high concentration of small speckles.



D16 Spice



D12 Vanilla



D17 Cedar



D14 Juta



D18 Saffron



D11 Musk



D20 Papaya



D15 Almond



D19 Pompei



D13 Oak





**THICKNESS**  
0.078 in  
(2 mm)



**ROLLS**  
6 ft 2 in x 45 ft 11 in  
(1.9 m x 14 m)



**TILES**  
24 in x 24 in  
(61 cm x 61 cm)



**WEIGHT**  
~1.00 lb/ft<sup>2</sup>  
(~4.9 kg/m<sup>2</sup>)



D02 Linen



D07 Palladium



D10 Moon



D09 Ash



D08 Air



D04 Elephant



D06 Island



D03 Seal



D05 Midnight



D01 Onyx

DHARMA TECHNICAL DATA

Performance Criterion	Test Method	Requirement*	Result**
Indoor Air Quality - CA Section 01350	CDPH v1.2-2017	-	Compliant
Indoor Air Quality - Greenguard Gold	UL 2821/UL 2818	-	Compliant
Modulus at 10% Elongation	ASTM D412	≥300 psi	≥300 psi
Static Coefficient of Friction (Neolite, Dry)	ASTM D2047	≥0.50	≥0.85
Durometer Hardness (Shore A)	ASTM D2240	≥85	90
Abrasion Resistance (H18 Wheel, 1000 g, 1000 Cycles)	ASTM D3389	≤ 1.0 g	0.05 g
Critical Radiant Flux	ASTM E648	≥0.45 W/cm² (Class 1)	≥0.45 W/cm² (Class 1)
Optical Density of Smoke	ASTM E662	≤450	≤450
Chemical Resistance ***	ASTM F925	≤ Slight Change	Compliant
Static Loading (Tested at 250 psi)	ASTM F970	≤0.005 in	0.000 in
Static Loading (Tested at 800 psi)	ASTM F970	-	0.002 in
Heat Resistance	ASTM F1514	ΔE ≤8.0	Compliant
Light Resistance	ASTM F1515	ΔE ≤8.0	Compliant
Tile Size	ASTM F2055	±0.45 mm	Compliant
Tile Squareness	ASTM F2055	≤0.254 mm	Compliant
Dimensional Starbility of Tile	ASTM F2199	≤0.15 %	Compliant
Impact Sound Insulation	ISO 10140-3	-	≈6 dB (ΔLw)

*\*\*For each individual test, the manufactured product is only required to meet any applicable requirement listed in the Requirement column.*

*\*\*\*A result obtained from testing during manufacturing controls and/or third-party verifications may vary between production lots, laboratories, methods and/or equipment, and as such any listed result in the Result column does not constitute representation or warranty as to any particular production lot. Mondo reserves the right to modify product design and/or specifications at any time without notice.*

*\*\*\*\*For the complete list of chemicals tested, concentrations and contact time, please communicate with Mondo's Technical Department.*



*All information provided in this binder is exact at the time of publishing. Mondo reserves the right to make changes as a result of new information, changes in process requirements and the availability of resources.*