



MASSETTO

Smooth surface with a handcrafted concrete design.



S01 Ivory



S02 Antique



S03 Greige



THICKNESS
0.118 in
(3 mm)



ROLLS
6 ft 2 in x 32 ft 9 in
(1.9 m x 10 m)



TILES
24 in x 24 in
(61 cm x 61 cm)



WEIGHT
~1.00 lb/ft²
(~4.9 kg/m²)



S04 Haze



S05 Cement



S06 Charcoal

Performance Criterion	Test Method	Requirement*	Result**
Indoor Air Quality - CA Section 01350	CDPH v1.2-2017	-	Compliant
Indoor Air Quality - Greenguard Gold	UL 2821/UL 2818	-	Compliant
Modulus at 10% Elongation	ASTM D412	≥300 psi	413.89 psi
Static Coefficient of Friction (Neolite, Dry)	ASTM D2047	≥0.50	≥0.80
Durometer Hardness (Shore A)	ASTM D2240	≥85	95
Abrasion Resistance (H18 Wheel, 1000 g, 1000 Cycles)	ASTM D3389	≤ 1.0 g	0.14 g
Impact Sound Transmission Reduction	ASTM E2179	-	≈10 dB (ΔIIC)
Critical Radiant Flux	ASTM E648	≥0.45 W/cm² (Class 1)	≥0.45 W/cm² (Class 1)
Optical Density of Smoke	ASTM E662	≤450	≤450
Chemical Resistance ***	ASTM F925	≤ Slight Change	Compliant
Static Loading (Tested at 250 psi)	ASTM F970	≤0.005 in	0.001 in
Static Loading (Tested at 800 psi)	ASTM F970	-	0.003 in
Heat Resistance	ASTM F1514	ΔE ≤8.0	Compliant
Light Resistance	ASTM F1515	ΔE ≤8.0	Compliant
Tile Size	ASTM F2055	±0.45 mm	Compliant
Tile Squareness	ASTM F2055	≤0.254 mm	Compliant
Dimensional Stability of Tile	ASTM F2199	≤0.15 %	Compliant
Resistance to Fungi	ASTM G21	-	No Growth

**Manufactured product is only required to meet the minimum listed requirement in the Requirement column.*

***Reported result listed in the Result column from manufacturing controls and/or third-party testing can vary between production lots, laboratories, methods and/or equipment, and as such do not constitute representations or warranties as to any particular production lot. Mondo reserves the right to modify product design and/or specifications at any time without notice.*



The MONDO CONTRACT GROUP

MONDO USA

MONDO AMERICA Inc. - Canada

artigo - Italy

www.mondocontractflooring.com
mondo@mondocontractflooring.com