

# dayGraphica® 490

Offset blanket optimized for folding carton and package printing.

**For Packaging and Commercial Sheetfed Presses** 

#### **Product Features**

- dayGraphica® 490 delivers performance in all packaging applications.
- Uniform thickness and consistency. Ideal surface for optimum ink transfer and reproducibility. Swell resistant surface resists cutting and washes up easily.
- Dense carcass construction maintains consistent gauge for longer life.
- Suitable for packaging and conventional sheetfed printing. Can also be used for metal decorating.

### Advantages of dayGraphica® 490

- Optimum ink transfer
- Smash resistant
- Durable
- Swell resistant





## dayGraphica® 490

Technical Information		
Color	Green	
Surface	Ground	
Face Compound	Solvent resistant blend	
Thickness	1.67 mm	1.96 mm
Compressibility @ 1MPa	0.12mm	0.13mm
Elongation	0.9%	0.9%
Hardness (°IRHD)	67	65

Application		
Sheetfed Commercial	**	
Sheetfed Packaging	***	
UV Sheetfed		
Hybrid Sheetfed		
Heatset Web		
Newspaper		
Coating/Varnishing		
Metal Decorating	**	

Microground Surface Layer Resists swell while delivering excellent reproduction




#### Closed-cell Compressible Layer

Solvent casting process ensures even thickness in machine and across direction

#### **Dense Carcass**

Made from the highest quality woven fabric to provide a stable print base



#### More products. Streamlined access. Greater results.

Flint Group offers a uniquely powerful combination of products, services and expertise; giving you access to the industry's broadest range of pressroom products.

#### Inks & Coatings. Pressroom Chemicals. Blankets. Sleeves. Consumables.

Rely on us for consistency, reliability and customer focus. Our aim is to make it easier for you to achieve your business goals. With Flint Group products in your pressroom, you can run your business with confidence and peace of mind.

You are welcome to contact us for further information.

The aim of our technical documents is to inform and advise our customers. The information provided herein is correct to the best of Flint Group's knowledge. No liability for any errors, facts or opinions is accepted. Customers must satisfy themselves as to the suitability of this product for their application. No responsibility for any loss as a result of any person placing reliance on any material contained herein will be accepted.

Product names followed by ® are trademarks registered by Flint Group.