

Non-Cushioned Technical Data Sheet



Curbside recyclable kraft paper mailer with reinforced side seams. This mailer has been constructed double-ply kraft paper to ensure durability and is an excellent choice for shipping non-fragile items.

Technical Data

| | | |
|------------------------------------|--|----------------------|
| Product Construction | 4 layers of 65 gsm natural kraft paper | |
| Typical Physical Properties | Note: The following technical information and data should only be considered representative or typical, and should not be used for specification purposes. | |
| Physical Property | Nominal Results | ASTM Test Method |
| Seal Flap Adhesion Strength | 1.0 lbf/in width | *Modified ASTM D3330 |

| Non-Cushioned mailer size | Outside Dimensions (in inches) | Inside Dimensions (in inches) |
|---------------------------|--------------------------------|-------------------------------|
| #NCM-0 | 7x9 | 6x9 |
| #NCM-5 | 12x16 | 11x16 |
| #NCM-6 | 14x16 | 13x16 |
| #NCM-7 | 14x19 | 13x19 |
| #NCM-9 | 18x19 | 17x19 |

| Breakdown of components processed by the material recovery facility (MRF). | Non-Cushioned Mailer Composition Table | |
|--|--|------------------------|
| | Material | Concentration (mass %) |
| | Kraft paper | 94.9 - 96.7 |
| Adhesives | 3.1 - 4.7 | |

01/2023

Storage – Store under normal conditions of 60° to 90°F (16° to 32°C) and 30 to 70% R.H in the original bag. Keep material packaged when stored and reseal package if opened. Avoid direct exposure to the UV light.

Shelf Life – To obtain best performance, use this product within 6 months from date of manufacturing.

For Additional Information – To request additional product information or to arrange for sales assistance, visit pregis.com/contact-us.

Technical Information – The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pregis believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use – The use and performance of this product are contingent upon a variety of factors that are beyond Pregis' control. The user is solely responsible for evaluating the product.