









Soho - Technical information, *Tiles and trims*

Tile collection performance based on industry standards.

Technical Information

	WATER ABSORPTION	ANSI / ISO - (%)	10% ≤E ≤18% - P4
	ABRASION RESISTANCE	ANSI / ISO	CLASS 0
	SCRATCH HARDNESS	ANSI / ISO - (Mohs)	GLOSSY 2 MATTE 2
	BREAKING STRENGTH	ANSI - (lbf) ISO - (N)	>230 >1000
	SHADE VARIATION		V1
	SLIP RESISTANCE	ANSI - DCOF (WET) ISO - R VALUE	GLOSSY N/A GLOSSY N/A MATTE N/A MATTE N/A
	CHEMICAL RESISTANCE	ANSI / ISO	CLASS B
	STAIN RESISTANCE	ANSI ISO	CLASS B CLASS 4
	FROST RESISTANCE	ANSI / ISO	NOT RESISTANT

Test values are based on ANSI / ISO standards according to: ANSI A137.1 Non-Vitreous P4 Class, ISO 13006 - L - Group BIII, EN 14411- L - Group BIII. Variances in test values can occur in different production lots.

Usage recommendation, *Tiles and trims*

Anatolia's recommendations for suitable applications.










Usage Recommendations*		GLOSSY GLAZED CERAMIC		MATTE GLAZED CERAMIC	
		WALL	FLOOR	WALL	FLOOR
INTERIOR	RESIDENTIAL	•		•	
	COMMERCIAL	•		•	
	HEAVY COMMERCIAL				
EXTERIOR	RESIDENTIAL / COMMERCIAL				

* These recommendations are not defined by ANSI/ISO standards.

Soho - Technical information, *Mosaics*

Tile collection performance based on industry standards.

Technical Information

	WATER ABSORPTION	ANSI / ISO - (%)	≤ 0.5				
	ABRASION RESISTANCE	ANSI / ISO	CLASS 0, 3, 4				
	SCRATCH HARDNESS	ANSI / ISO - (Mohs)	GLOSSY 5 MATTE 6 UNGLAZED 7				
	BREAKING STRENGTH	ANSI - (lbf) ISO - (N)	>275 >1220				
	SHADE VARIATION		V1				
	SLIP RESISTANCE	ANSI - DCOF (WET) ISO - R VALUE	GLOSSY ≥0.42 DRY (ID) GLOSSY R(-)	MATTE ≥0.42 DRY (ID) MATTE R(-)	UNGLAZED ≥0.65 (ID, IW, IW+, EW*, O/G*) UNGLAZED R10		
	CHEMICAL RESISTANCE	ANSI / ISO	CLASS A				
	STAIN RESISTANCE	ANSI ISO	CLASS A CLASS 5				
	FROST RESISTANCE	ANSI / ISO	PASS				

Test values are based on ANSI / ISO standards according to: ANSI A137.1 - Porcelain tile P1 Class, ISO 13006 - G - Bia Group, En 14411 - G - Bia Group. Variances in test values can occur in different production lots.

Usage recommendation, *Mosaics*

Anatolia's recommendations for suitable applications.

Usage Recommendations*		GLOSSY GLAZED PORCELAIN		MATTE GLAZED PORCELAIN		MATTE UNGLAZED PORCELAIN	
		WALL	FLOOR	WALL	FLOOR	WALL	FLOOR
INTERIOR	RESIDENTIAL	•	ID	•	ID	•	ID, IW, IW+, EW*, O/G*
	COMMERCIAL	•	ID	•	ID	•	ID, IW, IW+, EW*, O/G*
	HEAVY COMMERCIAL	•		•		•	
EXTERIOR	RESIDENTIAL / COMMERCIAL	•		•		•	ID, IW, IW+, EW*, O/G*

* These recommendations are not defined by ANSI/ISO standards.

DCOF Classifications per ANSI A326.3: (ID): Interior, Dry (IW): Interior, Wet (IW+): Interior, Wet Plus (EW): Exterior, Wet (O/G): Oils/Greases


* Factors other than the noted DCOF result must also be taken into consideration. Such factors include, but are not limited to, expected contaminants, drainage, surface texture, effect of structure on the DCOF measurement, number of grout joints, traction-enhancing features, and intended use in addition to the other criteria noted in standard ANSI A326.3

PLEASE NOTE THAT THE GLOSSY BEVELED ARABESQUE MOSAIC AND THE GLOSSY SCALLOP MOSAIC ARE ONLY RECOMMENDED TO BE USED ON THE WALL.

Soho - Technical information, *Patterned mosaics*

Tile collection performance based on industry standards.

Technical Information

	WATER ABSORPTION	ANSI / ISO - (%)	< 0.5
	ABRASION RESISTANCE	ANSI / ISO	CLASS 4
	SCRATCH HARDNESS	ANSI / ISO - (Mohs)	MATTE 6
	BREAKING STRENGTH	ANSI - (lbf) ISO - (N)	> 275 > 1220
	SHADE VARIATION		V1
	SLIP RESISTANCE	ANSI - DCOF (WET) ISO - R VALUE	MATTE ≥ 0.42 DRY (ID) MATTE R(-)
	CHEMICAL RESISTANCE	ANSI / ISO	CLASS A
	STAIN RESISTANCE	ANSI ISO	CLASS A CLASS 5
	FROST RESISTANCE	ANSI / ISO	PASS

Test values are based on ANSI / ISO standards according to: ANSI A137.1 - Porcelain tile P1 Class, ISO 13006 - G - Bia Group, En 14411 - G - Bia Group. Variances in test values can occur in different production lots.

Usage recommendation, *Patterned mosaics*

Anatolia's recommendations for suitable applications.

Usage Recommendations*

MATTE GLAZED PORCELAIN

APPLICATION		WALL	FLOOR
INTERIOR	RESIDENTIAL	•	ID
	COMMERCIAL	•	ID
	HEAVY COMMERCIAL	•	
EXTERIOR	RESIDENTIAL / COMMERCIAL	•	

* These recommendations are not defined by ANSI/ISO standards.

DCOF Classifications per ANSI A326.3: (ID): Interior, Dry (IW): Interior, Wet (IW+): Interior, Wet Plus (EW): Exterior, Wet (O/G): Oils/Greases

* Factors other than the noted DCOF result must also be taken into consideration. Such factors include, but are not limited to, expected contaminants, drainage, surface texture, effect of structure on the DCOF measurement, number of grout joints, traction-enhancing features, and intended use in addition to the other criteria noted in standard ANSI A326.3