CARMEN true tiles

ALTEA WHITE 7,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP | |
|-----------|-----------|----------------|---------|-----------------------|
| A031472 | 7,5X30 | 7,60 | REVESTI | and the second second |

| DIMENSIONS AND SURI | ACE PROPERTIES | | | | |
|---|-----------------|------------------------|--|--|--|
| Size, thickness, side straightness, flatness, orthogonality UNE-EN 14411 It accomplished all requerir | | | | | |
| | | | | | |
| PHYSICAL PRO | PERTIES | | | | |
| Water absorption capacity | EN ISO 10545-03 | >10% | | | |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² | | | |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test | | | |
| Cracking resistance | EN ISO 10545-11 | It stands the test | | | |
| Frost resistance | EN ISO 10545-12 | Not pass the test | | | |
| | | | | | |
| CHEMICAL PRO | OPERTIES | | | | |
| Resistance to acids | EN ISO 10545-13 | GLA | | | |
| Resistance to alcalis | EN ISO 10545-13 | GLA | | | |
| Resistance to cleaning products | EN ISO 10545-13 | GA | | | |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA | | | |
| Stains resistance | EN ISO 10545-14 | 5 | | | |





CARMEN true tiles

CALPE WHITE 7,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP | |
|-----------|-----------|----------------|---------|--|
| A031477 | 7,5X30 | 8,20 | REVESTI | |

| DIMENSIONS AND | SURFACE PROPERTIES | |
|---|--------------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
| | | |
| PHYSICA | L PROPERTIES | |
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Cracking resistance | EN ISO 10545-11 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |
| CHEMICA | L PROPERTIES | |
| Resistance to acids | EN ISO 10545-13 | GLA |
| Resistance to alcalis | EN ISO 10545-13 | GLA |
| Resistance to cleaning products | EN ISO 10545-13 | GA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA |
| Stains resistance | EN ISO 10545-14 | 5 |







TORELLO ALTEA WHITE 2X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP | |
|-----------|-----------|----------------|---------|--|
| A032179 | 2X30 | 0,00 | REVESTI | |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







TORELLO CALPE WHITE 2X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP | |
|-----------|-----------|----------------|---------|--|
| A032184 | 2X30 | 0,00 | REVESTI | |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







EDGE STICK ALTEA WHITE 1,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A032169 | 1,5X30 | 7,90 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







EDGE STICK CALPE WHITE 1,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A032174 | 1,5X30 | 7,90 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







ALTEA GREY 7,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP | and the second se |
|-----------|-----------|----------------|---------|---|
| A031475 | 7,5X30 | 8,30 | REVESTI | |

| DIMENSIONS AND SURFACE PROPERTIES | | | | | | |
|---|-----------------|------------------------|--|--|--|--|
| Size, thickness, side straightness, flatness, orthogonality UNE-EN 14411 It accomplished all requer | | | | | | |
| | | | | | | |
| PHYSICAL PF | ROPERTIES | | | | | |
| Water absorption capacity | EN ISO 10545-03 | >10% | | | | |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² | | | | |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test | | | | |
| Cracking resistance | EN ISO 10545-11 | It stands the test | | | | |
| Frost resistance | EN ISO 10545-12 | Not pass the test | | | | |
| | | | | | | |
| CHEMICAL PI | ROPERTIES | | | | | |
| Resistance to acids | EN ISO 10545-13 | GLA | | | | |
| Resistance to alcalis | EN ISO 10545-13 | GLA | | | | |
| Resistance to cleaning products | EN ISO 10545-13 | GA | | | | |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA | | | | |
| Stains resistance | EN ISO 10545-14 | 5 | | | | |







CALPE GREY 7,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP | a fair is an |
|-----------|-----------|----------------|---------|--|
| A031480 | 7,5X30 | 7,60 | REVESTI | |

| DIMENSIONS AND SURFACE PROPERTIES | | | | | |
|---|-----------------|------------------------|--|--|--|
| Size, thickness, side straightness, flatness, orthogonality UNE-EN 14411 It accomplished all re | | | | | |
| | | | | | |
| PHYSICAL | PROPERTIES | | | | |
| Water absorption capacity | EN ISO 10545-03 | >10% | | | |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² | | | |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test | | | |
| Cracking resistance | EN ISO 10545-11 | It stands the test | | | |
| Frost resistance | EN ISO 10545-12 | Not pass the test | | | |
| | | | | | |
| CHEMICA | L PROPERTIES | | | | |
| Resistance to acids | EN ISO 10545-13 | GLA | | | |
| Resistance to alcalis | EN ISO 10545-13 | GLA | | | |
| Resistance to cleaning products | EN ISO 10545-13 | GA | | | |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA | | | |
| Stains resistance | EN ISO 10545-14 | 5 | | | |







TORELLO ALTEA GREY 2X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A032182 | 2X30 | 0,00 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







TORELLO CALPE GREY 2X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A032187 | 2X30 | 0,00 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







EDGE STICK ALTEA GREY 1,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A032172 | 1,5X30 | 7,90 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







EDGE STICK CALPE GREY 1,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A032177 | 1,5X30 | 7,90 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test





CARMEN true tiles

ALTEA SKY 7,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP | |
|-----------|-----------|----------------|---------|--|
| A031474 | 7,5X30 | 8,20 | REVESTI | |

| DIMENSIONS AND SURFACE PROPERTIES | | | | | |
|---|-----------------|----------------------------------|--|--|--|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments | | | |
| | | | | | |
| PHYSICA | L PROPERTIES | | | | |
| Water absorption capacity | EN ISO 10545-03 | >10% | | | |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² | | | |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test | | | |
| Cracking resistance | EN ISO 10545-11 | It stands the test | | | |
| Frost resistance | EN ISO 10545-12 | Not pass the test | | | |
| | | | | | |
| CHEMICA | L PROPERTIES | | | | |
| Resistance to acids | EN ISO 10545-13 | GLA | | | |
| Resistance to alcalis | EN ISO 10545-13 | GLA | | | |
| Resistance to cleaning products | EN ISO 10545-13 | GA | | | |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA | | | |
| Stains resistance | EN ISO 10545-14 | 5 | | | |
| | | | | | |







CALPE SKY 7,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP | |
|-----------|-----------|----------------|---------|--|
| A031479 | 7,5X30 | 7,70 | REVESTI | |

| DIMENSIONS AND SURFACE PROPERTIES | | | | |
|---|----------------------------------|------------------------|--|--|
| Size, thickness, side straightness, flatness, orthogonality | It accomplished all requeriments | | | |
| | | | | |
| PHYSICA | L PROPERTIES | | | |
| Water absorption capacity | EN ISO 10545-03 | >10% | | |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² | | |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test | | |
| Cracking resistance | EN ISO 10545-11 | It stands the test | | |
| Frost resistance | EN ISO 10545-12 | Not pass the test | | |
| | | | | |
| CHEMICA | L PROPERTIES | | | |
| Resistance to acids | EN ISO 10545-13 | GLA | | |
| Resistance to alcalis | EN ISO 10545-13 | GLA | | |
| Resistance to cleaning products | EN ISO 10545-13 | GA | | |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA | | |
| Stains resistance | EN ISO 10545-14 | 5 | | |







TORELLO ALTEA SKY 2X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP | |
|-----------|-----------|----------------|---------|--|
| A032181 | 2X30 | 13,40 | REVESTI | |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







TORELLO CALPE SKY 2X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A032186 | 2X30 | 0,00 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







EDGE STICK ALTEA SKY 1,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A032171 | 1,5X30 | 7,50 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







EDGE STICK CALPE SKY 1,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A032176 | 1,5X30 | 0,00 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test





CARMEN true tiles

ALTEA IVORY 7,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP | |
|-----------|-----------|----------------|---------|--|
| A031473 | 7,5X30 | 8,20 | REVESTI | |

| DIMENSIONS AND SURFACE PROPERTIES | | | | | | |
|--|---------------------------------------|------------------------|--|--|--|--|
| Size, thickness, side straightness, flatness, orthogonality UNE-EN 14411 It accomplished all requering | | | | | | |
| | · · · · · · · · · · · · · · · · · · · | | | | | |
| PHYSICAL PI | ROPERTIES | | | | | |
| Water absorption capacity | EN ISO 10545-03 | >10% | | | | |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² | | | | |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test | | | | |
| Cracking resistance | EN ISO 10545-11 | It stands the test | | | | |
| Frost resistance | EN ISO 10545-12 | Not pass the test | | | | |
| | | | | | | |
| CHEMICAL P | ROPERTIES | | | | | |
| Resistance to acids | EN ISO 10545-13 | GLA | | | | |
| Resistance to alcalis | EN ISO 10545-13 | GLA | | | | |
| Resistance to cleaning products | EN ISO 10545-13 | GA | | | | |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA | | | | |
| Stains resistance | EN ISO 10545-14 | 5 | | | | |







CALPE IVORY 7,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP | |
|-----------|-----------|----------------|---------|--|
| A031478 | 7,5X30 | 7,90 | REVESTI | and the second sec |

| DIMENSIONS AND | SURFACE PROPERTIES | |
|---|--------------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
| PHYSICA | L PROPERTIES | |
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Cracking resistance | EN ISO 10545-11 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |
| CHEMICA | L PROPERTIES | |
| Resistance to acids | EN ISO 10545-13 | GLA |
| Resistance to alcalis | EN ISO 10545-13 | GLA |
| Resistance to cleaning products | EN ISO 10545-13 | GA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA |
| Stains resistance | EN ISO 10545-14 | 5 |







TORELLO ALTEA IVORY 2X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP | |
|-----------|-----------|----------------|---------|--|
| A032180 | 2X30 | 0,00 | REVESTI | |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







TORELLO CALPE IVORY 2X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP | |
|-----------|-----------|----------------|---------|--|
| A032185 | 2X30 | 0,00 | REVESTI | |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







EDGE STICK ALTEA IVORY 1,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A032170 | 1,5X30 | 7,90 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







EDGE STICK CALPE IVORY 1,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A032175 | 1,5X30 | 7,90 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







ALTEA TAUPE 7,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP | |
|-----------|-----------|----------------|---------|--|
| A031476 | 7,5X30 | 7,50 | REVESTI | Carlos Ca |

| DIMENSIONS AND | SURFACE PROPERTIES | |
|---|--------------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
| | | |
| PHYSICA | L PROPERTIES | |
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Cracking resistance | EN ISO 10545-11 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |
| | | |
| CHEMICA | L PROPERTIES | |
| Resistance to acids | EN ISO 10545-13 | GLA |
| Resistance to alcalis | EN ISO 10545-13 | GLA |
| Resistance to cleaning products | EN ISO 10545-13 | GA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA |
| Stains resistance | EN ISO 10545-14 | 5 |







CALPE TAUPE 7,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP | |
|-----------|-----------|----------------|---------|--|
| A031481 | 7,5X30 | 8,70 | REVESTI | |

| DIMENSIONS AND | SURFACE PROPERTIES | |
|---|--------------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
| | | |
| PHYSICA | L PROPERTIES | |
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Cracking resistance | EN ISO 10545-11 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |
| CHEMICA | L PROPERTIES | |
| | | |
| Resistance to acids | EN ISO 10545-13 | GLA |
| Resistance to alcalis | EN ISO 10545-13 | GLA |
| Resistance to cleaning products | EN ISO 10545-13 | GA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA |
| Stains resistance | EN ISO 10545-14 | 5 |







TORELLO ALTEA TAUPE 2X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A032183 | 2X30 | 15,00 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







TORELLO CALPE TAUPE 2X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A032188 | 2X30 | 0,00 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







EDGE STICK ALTEA TAUPE 1,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A032173 | 1,5X30 | 7,90 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test







EDGE STICK CALPE TAUPE 1,5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A032178 | 1,5X30 | 7,90 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance

EN ISO 10545-12

Not pass the test



