

Technical Specifications - White | Bone

CHARACTERISTICS	STANDARD	DECLARED ASTM
Dimensions	ISO 10545-2	± 0.5%
Water Absorption	ISO 10545-3	<=0.5%<E<=3%
Resistance to Surface Abrasion	ISO 10545-7	CLASS 4
Chemical Resistance	ISO 10545-13	GLA
Flatness	ISO 10545-2	± 0.5%
Scratch Hardness	67-101	5
Crazing Resistance	ISO 10545-11	Accomplish
Resistance to Stains	ISO 10545-14	5
Chemical Resistance Swimmingpool	ISO 10545-13	GA
Slip Resistance	41901 EX	Class 0
Frost Resistance	ISO 10545-12	Accomplish
Resistance to Thermal Shock	ISO 10545-9	Accomplish
Breaking Strength	ISO 10545-4	>=125 lbf

Technical Specifications - Flamingo | Aquamar

CHARACTERISTICS	STANDARD	DECLARED ASTM
Dimensions	ISO 10545-2	± 0.5%
Water Absorption	ISO 10545-3	<=0.5%<E<=3%
Resistance to Surface Abrasion	ISO 10545-7	CLASS 3
Chemical Resistance	ISO 10545-13	GLA
Flatness	ISO 10545-2	± 0.5%
Scratch Hardness	67-101	5
Crazing Resistance	ISO 10545-11	Accomplish
Resistance to Stains	ISO 10545-14	5
Chemical Resistance Swimmingpool	ISO 10545-13	GA
Slip Resistance	41901 EX	Class 0
Breaking Strength	ISO 10545-4:9	>30N/ mm ²
Frost Resistance	ISO 10545-12	Accomplish
Resistance to Thermal Shock	ISO 10545-9	Accomplish
Breaking Strength	ISO 10545-4	>=125 lbf

Packaging Info

Size	SF per carton	PC per carton	BX per pallet
5.8"x5.8"	498.15	44	70